

The wheel tracking test is used for determining the susceptibility of Hot Mix

Asphalt (HMA) to deformation under load by measuring the rut depth formed by

repeated passes of a loaded wheel at a fixed temperature.